

Properties (dry)		Value	Units	Method
Viscosity	RV in formic acid, nominal	46	---	ASTM D789
	VN at 0.5% in sulfuric acid, nominal	147	mL/g	ISO 307
	VN at 0.5% in formic acid, nominal	134	mL/g	ISO 307
	RV at 1% in sulfuric acid, nominal	2.65	---	---
Physical	Density	1.14	g/cm ³	ISO 1183
	Mold Shrinkage, 2.0 mm, Parallel	1.8	%	ISO 294-4
	Mold Shrinkage, 2.0 mm, Transverse	1.7	%	ISO 294-4
	Water Absorption - 24 hours	1.7	%	ISO 62
	Water Absorption - Equilibrium @ 50% RH	2.6	%	ISO 62
Mechanical	Tensile Strength at Yield	84	MPa	ISO 527
	Elongation at Yield	4.4	%	ISO 527
	Elongation at Break	30	%	ISO 527
	Tensile Modulus	3100	MPa	ISO 527
	Flexural Modulus	2900	MPa	ISO 178
	Flexural Strength	94	MPa	ISO 178
	Notched Charpy at 23°C	5.0	kJ/m ²	ISO 179
	Notched Charpy at -30°C	4.2	kJ/m ²	ISO 179
	Unnotched Charpy at 23°C	NB	kJ/m ²	ISO 179
	Unnotched Charpy at -30°C	NB	kJ/m ²	ISO 179
Thermal	Notched Izod at 23°C	5.0	kJ/m ²	ISO 180
	Melting Temperature, 10°C/min	261	°C	ISO 11357
	HDT at 0.45 MPa	185	°C	ISO 75
	HDT at 1.80 MPa	62	°C	ISO 75
	CLTE, 2.0 mm, Parallel, 23 - 55 °C	0.9	10 ⁻⁴ /°C	ISO 11359
Electrical	CLTE, 2.0 mm, Transverse, 23 - 55 °C	0.9	10 ⁻⁴ /°C	ISO 11359
	Dielectric Strength, 1.0 mm	18	kV/mm	UL 746A
	Comparative Tracking Index, 3.0 mm	600	volts	IEC 60112
	High Voltage Arc Tracking Rate (HVTR)	PLC 0	---	UL 746A
Flammability	High Volt, Low Current Arc Resistance	PLC 5	---	UL 746A
	Flame Rating at 0.40 mm	V-2	---	UL 94
	Flame Rating at 0.71 mm	V-2	---	UL 94
	Flame Rating at 1.5 mm	V-2	---	UL 94
	Flame Rating at 3.0 mm	V-2	---	UL 94
	Glow-Wire Flammability at 0.71 mm	960	°C	IEC 60695
	Glow-Wire Flammability at 1.5 mm	960	°C	IEC 60695
Glow-Wire Flammability at 3.0 mm	960	°C	IEC 60695	

Product Description

INVISTA U4630HSL is a heat-stabilized, lubricated PA66 resin in natural color. The heat stabilizer system has been designed to provide excellent property retention in high temperature applications. It is lubricated internally and externally.

General Information

Material Status

Commercial: Active

Availability

North America, South America, Europe, Asia

Features

Excellent property retention at elevated temperatures; improved flow and processability.

Classification

ASTM D4066 classification PA0121

RoHS

No intentional additives or ingredients used in U4630HSL are among those in the European directive 2011/65/EC (RoHS), as amended.

Process Guidelines for Molding

Drying Temperature	80 °C
Drying Time*	3 - 4 hours
Barrel Temperatures	
Rear	250 - 270 °C
Middle	270 - 290 °C
Front	270 - 290 °C
Nozzle	270 - 290 °C
Processing Temperature (melt)	280 - 295 °C
Mold Temperature	50 - 90 °C
Back Pressure**	2 - 10 bar
Vent Depth	0.007 - 0.04 mm
Cushion (range)	4 - 6 mm
Suggested Moisture (max)	0.20 wt%
Suggested Moisture (min)	0.10 wt%
Screw Speed	75 - 180 rpm

* Initial moisture below 0.25 wt%. Use dehumidified air.

** Melt pressure

INVISTA Nylon Polymer

Additional Information: NISP@INVISTA.com

Website: NylonPolymer.INVISTA.com

Issue Date: June 2019

Product Data Sheet Disclaimer

This Product Data Sheet relates only to the identified product and any identified uses. It is based on information available as of June 2019. Additional information may be needed to evaluate other uses of the product, including use of the product in combination with any materials or in any processes other than those specifically referenced. THIS PRODUCT DATA SHEET DOES NOT CONTAIN A COMPLETE STATEMENT OF, AND DOES NOT CONSTITUTE A REPRESENTATION, WARRANTY OR GUARANTY WITH REGARD TO, A PRODUCT'S CHARACTERISTICS, USES, QUALITY, MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR THE SUITABILITY, SAFETY, EFFICACY, HAZARDS OR HEALTH EFFECTS OF THE PRODUCT, WHETHER USED SINGULARLY OR IN COMBINATION WITH ANY OTHER PRODUCT, EXCEPT TO THE EXTENT REQUIRED BY THE RELEVANT LAW AND REGULATIONS. Nothing contained in this Product Data Sheet shall be construed to modify any of the terms under which the product was sold by INVISTA.